
DESCRIPTION:

Nukote XT plus is a fast set, rapid curing modified polyurea designed for use in application on concrete, steel or other substrates for protection against high acidic, alkaline chemicals in combination with moderate heat or pressure. Nukote XT plus is designed for acid and base environments and is a 100% solids flexible, aromatic, two component spray applied polyurethane polyurea. Nukote XT plus is suitable where anaerobic and aerobic waste by-products combined with elevated temperatures are expected. The product is commonly specified in conjunction with other Nukote products in monolithic compositions or as a geotextile composite for applications in immersion as liner or in secondary containment of chemical storage tanks. This aromatic polyurea elastomer exhibits good long term chemical resistance, thermal stability and UV resistance.

FEATURES:

- 100% solids with zero VOC
- Fast reactivity and cure time resulting in almost immediate return-to-service time
- Performs in constant process temperatures from -40 °F to 250 °F (-40 °C to 120 °C)
- Maintains high physical properties on weathering
- Seamless, resilient, flexible and tough
- Superior chemical resistance –acids and bases (consult NCSI)
- Good corrosion protection in chemical immersion
- Low permeability waterproofing and protective membrane

TYPICAL USES:

- Water, waste water and storm water plants and infrastructures
- Mining containment, process equipment and distribution
- Oil & gas and petrochemical containment and distribution
- Treated water and desalination process, containment and distribution
- Power generation; thermal, hydro, gas and nuclear process and containment
- Primary & secondary containment of most liquid systems
- Landfill containment.

COLORS:

Standard medium grey only. Custom colors, blended to match any RAL number, are available upon request subject to minimum quantity.

PACKAGING:

400-liter drum sets, shipped in metal drums of 200-liters each of side A and side B.
40-liter kits, shipped in metal pails 20-liters each of side A and side B.

COVERAGE:

Nukote XT plus may be applied at any rate to achieve the desired thickness.
Calculation for theoretical coverage: 40 Ft²/gal @ 40 mils (1 m²/liter @ 1mm).

STORAGE:

Nine to twelve months in factory delivered, unopened drums kept at 77° F (25° C). Keep away from extreme heat, freezing, and moisture. The use of drum heaters is encouraged to reduce material viscosity at low temperatures.

NUKOTE ARABIA COATING SYSTEMS

DAMMAM SECOND INDUSTRIAL CITY

P.O. BOX: 31149 DAMMAM 31952 SAUDI ARABIA

www.nukotearabia.com

Isocyanate or A side is sensitive to thermal cycling and low temperature if exposed and may require heating and filtering in extreme case of crystallization. Contact Nukote Technical service for the procedure

TECHNICAL DATA (All values @ 77 °F / 25 °C)	Metric
Solids by volume (ASTM D2697)	100%
Volatile organic compounds (ASTM D2369)	0 gm/ lit
Theoretical coverage	1m ² / lit @ 1mm
Specific Gravity of materials (ASTM D792)	A: 1.12, B: 1.01 kg/ liter
Viscosity at 158 °F/70 °C in cps ±10% (ASTM D4878)	A-50 ± 20, B-50 ± 20
Shelf life @ 77 °F /25 °C	09 to 12 Months
Tensile strength (ASTM D412-C)	14 to 21 MPa
Elongation (ASTM D412-C)	50-100 %
Hardness (ASTM D2240)	45 to 50 Shore D
Flexibility (2mm mandrel ASTM D522)	Pass
Water vapour transmission rate (ASTM E96)	0.2 to 0.3gms/hr-m ²
Water absorption -24 hours (ASTM D570)	~1%
Crack Bridging @ -13 °F/-25 °C (ASTM C1305), 25 cycles	Pass
Tear strength (ASTM D642)	40 to 45 Kn/m
Impact Resistance (ASTM G14), No Holidays	> 16 J (N-m)
Fire Rating (ASTM E108)	Meets Class A for Flame spread
Flash point Pensky Martin	>93 °C
Service temperature (Dry)	-40 °C to 120 °C
Abrasion Resistance (ASTM D4060) weight loss	< 20 mg loss Taber CS 17 wheel 1Kg/1000 rev
PROCESSING PROPERTIES (Under standard lab conditions)	
Mix Ratio V/V	1:1
Gel time	6 to 20 seconds
Tack free time (DFT & Temperature dependent)	30 to 45 Seconds
Post cure time	24 hours

NUKOTE ARABIA COATING SYSTEMS

DAMMAM SECOND INDUSTRIAL CITY

P.O. BOX: 31149 DAMMAM 31952 SAUDI ARABIA

www.nukote-arabia.com

Properties and values are highly dependent on equipment, spray gun, mix chamber temperature, pressure and related parameters. Variations are possible and expected. Values included above are per NCSI standard lab practices & methodology of draw down film at various dry film thicknesses.

MIXING:

Nukote XT plus might not be diluted under any circumstance. Thoroughly mix Nukote XT plus Part B resin material with air driven power equipment until a homogeneous mixture and color is obtained. Always use dedicated spray equipment.

SURFACE PREPARATION:**Concrete:**

The surface of a concrete subfloor should be dry, smooth, structurally sound and free of depression, scale, or foreign deposits of any kind. Remove all curing compounds. Abrasive blast, sweep blast or water blast to remove all latent material and expose voids. Use a good quality epoxy filler or mortar for void and spall filling, skim coat or repairs. Prime, fill imperfections in the substrate surface to limit out-gassing. All concrete substrates, on or below grade level should be tested for moisture content. On-grade or below-grade concrete floors or slabs should have a moisture barrier installed to protect from ground moisture. The surface preparation of concrete should meet and conform to Joint NACE 6/SSPC-SP 13 standards and achieve a concrete surface profile of CSP 3 to CSP 6 as per ICRI Guideline No.03732 for optimum performance.

If concrete surfaces known to, or likely to suffer from, rising dampness, potential osmosis problems or have a moisture content > 5%, concrete has to be treated with Nukote HLT*.

If concrete is < 28-days old and rush application is desired, concrete has to be treated with Nukote HLT*.

If concrete surfaces known to, or likely carbonation, concrete has to be treated with Nukote HLT*.

Steel:

All steel surfaces should be clean and free from contamination. The surface should be assessed and treated in accordance with ISO 8504, Abrasive blast the surface to minimum NACE-2/SSPC SP-10/Sa 2.5, as per ISO 8501-1, for a visual assessment of surface cleanliness with an anchor profile of 3 to 4 mils (75 -100 microns). Soluble salts must be removed to an acceptable level.

Where extended coating performance on metal surfaces is desirable with an extended window of application prior to surface oxidation, metal surfaces are recommended to be treated using Premera CW* range.

Where abrasive blasting is not permissible due to spark generation, metal surfaces are recommended to be cleaned using Premera CW-VB*.

** Refer to products' Technical Data Sheets for further details*

***Refer to NCSI surface preparation manual for detailed procedures for different types of substrates.*

NUKOTE ARABIA COATING SYSTEMS

DAMMAM SECOND INDUSTRIAL CITY

P.O. BOX: 31149 DAMMAM 31952 SAUDI ARABIA

www.nukotearabia.com

TDS-NA-XT plus 0116-SA

PRIMING:

Following correct preparation, the substrate must be primed.

Concrete

For dry conditions, sound, dry concrete, prime using Nukote Polyprime I/II* or Nukote Metal Prime II*. If moisture content of concrete exceeds 5%, prime using Premera MI Prime*.

Steel

For steel surfaces, prime using Nukote Metal Prime II** or Premera AE T7/AE T7 LF*.

Other Substrates

Painted or unpainted iron; aluminium, copper and other metals; hot rolled steel, cold rolled steel, stainless steel; powder coated and galvanized surfaces; wood, rubber, plastic, fiberglass and glass, prime using Nukote Metal Prime II* or Premera AE T7/AE T7 LF*

**Refer to products' Technical Data Sheets for further details.*

APPLICATION:

Must be applied utilizing high-pressure, heated plural component 1:1 spray proportioning equipment, such as Graco Reactor, or equivalent, capable of delivering materials without loss of pressure or drop in temperature for the appropriate hose length on a consistent basis.

Both Part-A and Part-B material should be preconditioned at 26-33°C before application. Recommended surface temperature must be at least 3°C above the dew point.

Both Part-A and Part-B materials should be sprayed at a minimum of 2000 psi and at temperatures above 70°C. Adequate pressure and temperature should be maintained at all times.

For optimum performance, the substrate should be abrasive blasted. Concrete substrates should be allowed to cure for a minimum of 28 days. On concrete, Nukote ST should always be applied over a suitable primer for maximum adhesion.

On horizontal surface applications, a texture "stipple" coat can be applied for non-skid purposes, after reaching the initial desired film thickness.

Recommended DFT's are a subjected to functionality and exposure requirements. Please review your specific design with Nukote technicians.

Nukote ST should be sprayed in smooth, multidirectional passes to improve uniform thickness and appearance.

Application of subsequent layers should be within the over coating open window time. If maximum over-coating time is exceeded, it is necessary to activate the previous layer using Nukote IC PRIME U*.

**Refer to products' Technical Data Sheets for further details.*

EQUIPMENT CLEAN UP:

Cured product may be disposed of without restriction. Uncured Isocyanate and resin portions should be mixed together and disposed of in accordance with local regulations. Containers should be disposed of according to local environmental laws and ordinances.

NUKOTE ARABIA COATING SYSTEMS

DAMMAM SECOND INDUSTRIAL CITY

P.O. BOX: 31149 DAMMAM 31952 SAUDI ARABIA

www.nukotearabia.com

TDS-NA-XT plus 0116-SA

LIMITATIONS:

Do not open until ready to use, and store in a sealed container after opening. Adding a nitrogen blanket is strongly recommended for the 'A' component when storing after opening.

Due to its aromatic composition, Nukote ST will tend to yellow or darken in color and will become flat after exposure to UV light. A topcoat can be applied to Nukote ST within six hours of application with an aliphatic polyurethane/polyurea coating for a colorfast finish.

WARNING:

This product contains Isocyanate and curatives

CHEMICAL RESISTANCE:

Each Nukote product formulation has varying levels of resistance to specific chemicals. Please review the chemical immersion test data included in the Nukote Test Book for general resistance to specific chemicals at specific concentration levels. Chemical concentrations are complex and when combined with temperatures above ambient levels this complexity increases exponentially. Contact Nukote Technical Personnel for specific recommendations for chemical resistance prior to specifying these products in this application type. Consult with NCSI for more details on product and chemical resistance. The following chart is the results of Polyurea immersed in chemicals and tested as per modified ASTM D 3912.

Chemicals	Resistance	Chemicals	Resistance
Hydrochloric acid 15%	R	Sodium Hydroxide 50%	R
Sulphuric Acid 50%	R	Ammonium Hydroxide 20%	R
Phosphoric Acid 15%	R	Pottasium hydroxide 20%	R
Acetic Acid 10%	R	Sodium Bicarbonate 30%	R
Nitric Acid 25%, HF 10%	R	Sodium Hypochlorite 14%	R
Water @ 176 °F (80 °C)	R	Calcium Hydroxide 30%	R
Diesel	R	Hydrogen sulphide (gas)	R
Hydraulic Oil	R	Sewage	R
Perchloric acid 60%	R	Hydrogen proxide	R

R = Resistant RC = Slight surface change or discolouration with no loss of hardness
Contact NCSI for more on chemical resistance details and list of chemicals tested

NUKOTE ARABIA COATING SYSTEMS

DAMMAM SECOND INDUSTRIAL CITY

P.O. BOX: 31149 DAMMAM 31952 SAUDI ARABIA

www.nukotearabia.com

WARRANTIES AND DISCLAIMERS:

Nukote Coating Systems warrants that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product is dependent upon the proper mixture and application of the components by the applicator. Nukote Coating Systems has no role in the application of the finished polymer other than to manufacture and supply its two components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of plural component equipment and application of plural component materials. There are no warranties that extend beyond the description on the face of this instrument, except when provided in writing, directly by Nukote Coating Systems and executed under seal by a company officer.

.

NUKOTE ARABIA COATING SYSTEMS

DAMMAM SECOND INDUSTRIAL CITY

P.O. BOX: 31149 DAMMAM 31952 SAUDI ARABIA

www.nukotearabia.com

TDS-NA-XT plus 0116-SA